



Géométrie Geometria	Applications Applicazioni	Avances f (mm/trs) Avanzamento f (mm/giro)
.WA. 	tronçonnage, gorges, finitions de gorges, arête vive troncatura, gole, finitura di gole, larghezze parziali	↓ 0,07 - 0,25



## Conditions de coupe

Parametri di taglio

Matière à usiner Materiale da lavorare	Dureté Durezza Brinell (HB)	Vitesse de coupe $v_c$ (m/min) Velocità di taglio $v_c$ (m/min)		
		K10	DD26	
N Alliage d'aluminium Leghe d'alluminio	traitem. impossible non temprabili	30-80	1000-600	1000-600
	traitement possible temprabili	80-120	400-220	400-220
Alliage de fonte d'aluminium Leghe d'alluminio fuso	traitem. impossible non temprabili	80	1000-600	1000-600
	traitement possible temprabili	100	600-300	600-300